



2300 Exterior Remanufactured Semi-Gloss Latex Finish

Paint Recycling, Inc.
"Quality Remade"

CHARACTERISTICS:

- Remanufactured
- Environmentally Preferred
- Excellent Quality
- Exterior Latex Semi Gloss Finish
- Excellent Adhesion
- Weather Resistant
- Durable
- Easy Application
- Soap & Water Clean-Up
- Low Odor

PHYSICAL PROPERTIES:

- Finish: Semi-Gloss
- Sheen @ 60° ----- 45-50%

VOLUME SOLIDS:

- Approximately 35%

COLORS:

- Available in many interior stock colors.
- Custom colors available on request.

VISCOSITY:

- Package Viscosity 90-100 KU

PERFORMANCE PROPERTIES:

Approximately 300-400 sq. ft. per gallon depending on substrate and application method, porosity and surface texture. Approximate coverage for each coat.

RECOMMENDED DRY FILM THICKNESS

- 1.5 to 1.7 Mils DFT

MILDEW RESISTANT:

This coating contains agents that inhibit the growth of mildew on the surface of this coating.

DRYING TIME:

- To Touch ----- 30-60 minutes
- To Re-coat ----- 5-6 hours
- Lower temperatures, humidity, thicker film

PREPARATION & PRIMING

BLOCK: (Prime with appropriate primer) Allow new block to cure before Application of primers and finish coats. Remove loose mortar and patch all voids with appropriate patching or caulking material. Clean surface to remove dirt, efflorescence, grease, oil, wax, mildew or other foreign matter.

CONCRETE: (Prime with appropriate primer) Allow new concrete to cure for 60 days before application of primer and finish coats. Patch all voids with the appropriate patching or caulking material. Power-wash all tilt-up and poured in place concrete to remove any bond-breakers or other construction residue. Clean the surface to remove any dirt, efflorescence, grease, oil, wax, mildew or other foreign material.

METAL: (Prime with appropriate primer) Apply finish to primed or previously painted metal with no visible rust. Scrape, power tool clean and sand the surface to remove any dirt, grease, oil, rust, mill scale, loose shop primer or other foreign matter.

STUCCO: (Prime with appropriate primer) Allow new stucco to cure before application of finish coats. Patch all voids with the appropriate patching or caulking material. Clean the surface to remove any dirt, efflorescence, grease, oil, wax, mildew or other foreign material. Best results are obtained when surface is back-rolled.

WOOD: (Prime with appropriate primer) Patch all voids with the appropriate patching or caulking material. Clean the surface to remove any dirt, grease, oil, wax, mildew or other foreign matter.

PREVIOUSLY PAINTED SURFACES: Patch all voids with the appropriate patching or caulking material. Wash, rinse, scrape, sand and clean the surface to remove any chalk, dirt, grease, oil, wax, mildew, loose paint or other foreign material.

APPLICATION:

METHODS: Product may be applied with brush, roller or airless sprayer. Maintain a "wet edge" and apply coating uniformly.

Do not apply where material, air or surface Temperature is below 50° F Surfaces and ambient temperatures must be between 48° F and 100° F, 5° above dew point and remain above 48° F for a minimum of four hours after application. All paint products should be tested for adhesion, appearance, color and compatibility prior to application.

THINNING: Product intended for use at package Consistency. If thinning is desired, do not thin more than 1/2 pint per gallon.

CLEAN-UP: Clean up equipment and area with soapy water.

PERSONAL: Paint may be irritating to eyes, nose and skin. Avoid contact with eyes. In case of eye contact, flush at least fifteen minutes and call a physician immediately.

STORAGE: Keep from freezing store above 50° F

MAXIMUM VOC:
<150 GRAMS PER LITER
<2.08 POUNDS PER GALLON

CAUTION: Avoid contact with eyes, skin and clothing. Do not take internally. Wash thoroughly after handling. Close container after each use. For additional safety information consult the Material Safety Data Sheet (MSDS)

KEEP OUT OF REACH OF CHILDREN. USE ONLY WITH ADEQUATE VENTILATION.